



TECHNICAL SPECIFICATIONS

TYPE:
Hot-Rolled bars of equal angles having round edges (Equal Angles)

STEEL GRADE:
- S235JR according to ELOT-EN 10025 (St 37-2 according to DIN 17100)
- S275JR according to ELOT-EN 10025 (St 44-2 according to DIN 17100)

FORM - DIMENSIONS:
Straight bars with diameter from 20 to 100mm and side thickness from 3 to 12mm

LENGTH - TOLERANCE:
Bar length 6m - 12m with tolerance -0 / +100mm

PACKING - WEIGHT:
Bundles weighing approximately 2,500kg


DIMENSIONS - WEIGHT - TOLERANCES:
According to EN 10056 (DIN 1018)

EQUAL ANGLES

Hot-Rolled bars of equal angles having round edges



Equal angle bars are manufactured at SIDENOR's factory in Thessaloniki, at a length of 6 metres, with a leg length ranging from 20mm to 50mm and with a leg thickness of between 3mm and 6mm. Moreover, STOMANA's factory in Bulgaria manufactures angles with a leg length from 60mm to 100mm and a leg thickness from 6mm to 12mm, at lengths of 6 and 12 metres. Angles are products with a wide range of applications, being used in fencing, as support piles for sheds in vineyards, for sheds and roofs, coachworks, and for the construction of steel power towers, etc.



SALES OFFICES

www.sidenor.gr

CENTRAL OFFICES SIDENOR SA

33, Amaroussiou-Halandriou str.
GR-15125, Maroussi, Athens, Greece
Tel.: (+30) 210-6787854,
(+30) 210-6787700
Fax: (+30) 210-6787740

THESSALONIKI PLANT SIDENOR SA

12th klm National Road
Thessaloniki-Veria GR-57008,
Ionia, Thessaloniki, Greece
Tel.: (+30) 2310-790133
Fax: (+30) 2310-790144



STEEL CHEMICAL COMPOSITION & MECHANICAL PROPERTIES

STEEL GRADE	CHEMICAL COMPOSITION			MECHANICAL PROPERTIES		
	C (%) max	P (%) max	S (%) max	YIELD STRENGTH (N/mm ²) min	TENSILE STRENGTH (N/mm ²)	ELONGATION 5d ₀ , (%) min
S235JR (St 37-2)	0.170	0.040	0.040	235	360 - 510	26
S275JR (St 44-2)	0.210	0.040	0.040	275	410 - 560	23
S355J2 (St 52-3)	0.200	0.030	0.030	355	470 - 630	22

DIMENSIONS, WEIGHTS & TOLERANCES OF EQUAL ANGLES

DIMENSIONS (mm)	DIMENSIONS (mm)						NOMINAL CROSS SECTION (cm ²)	NOMINAL WEIGHT (kg/m)	NOMINAL SURFACE AREA (m ² /m)
	a (mm)	PERMISSIBLE DEVIATION FOR (a) (mm)	s* (mm)	PERMISSIBLE DEVIATION FOR (s) (mm)	r1 (mm)	r2 (mm)			
20x20x3	20	±1.00	3	±0.50	3.5	2.0	1.12	0.88	0.077
25x25x3	25		3		3.5	2.0	1.42	1.12	0.097
30x30x3 30x30x4	30		3 4		5.0	2.5	1.74 2.27	1.36 1.78	0.116
35x35x3 35x35x4	35		3 4		5.0	2.5	2.04 2.67	1.60 2.10	0.136
40x40x3 40x40x4 40x40x5	40		3 4 5		6.0	3.0	2.35 3.08 3.79	1.84 2.42 2.97	0.155
45x45x4 45x45x5	45		4 5		7.0	3.5	3.49 4.30	2.74 3.38	0.174
50x50x4 50x50x5 50x50x6	50		4 5 6		7.0	3.5	3.89 4.80 5.69	3.06 3.77 4.47	0.194
60x60x5 60x60x6	60		5 6		8.0	4.0	5.82 6.91	4.57 5.42	0.233
65x65x6 65x65x7	65		6 7		9.0	4.5	7.40 8.70	5.90 6.80	0.252
70x70x6 70x70x7	70		6 7		9.0	4.5	8.13 9.40	6.38 7.38	0.272
75x75x6 75x75x7 75x75x8	75	6 7 8	10.0	5.0	8.70 10.10 11.50	6.90 7.94 9.03	0.291		
80x80x7 80x80x8 80x80x10	80	7 8 10	10.0	5.0	10.80 12.30 15.10	8.49 9.66 11.90	0.311		
90x90x7 90x90x9	90	7 9	11.0	5.5	12.20 15.50	9.61 12.20	0.351		
100x100x7 100x100x8 100x100x10 100x100x12	100	7 8 10 12	12.0	6.0	13.60 15.50 19.20 22.70	10.80 12.20 15.10 17.80	0.390		

* Special thickness can be available upon request